



# IMPERMEABILIZANTE ACRILICO INCOLORO

## SALES FORMAT

15L, 4L



### DESCRIPTION

Waterproof coating based on a mixture of pure acrylic and elastic self-crosslinking emulsions, which, when dry, provides a continuous coating, with a thick layer, which prevents any water filtration. Its high flexibility and tensile strength perfectly withstands expansion and contraction of the treated surface. Due to its cross-linking by UV radiation, it is highly resistant to soiling. Due to its high resistance to alkalinity and water, flexibility and durability, as well as its resistance to expansion and contraction movements, high adhesion and light fastness, it is ideal for preventing water seepage.

### SCOPE OF APPLICATION

Exterior. Cement mortar. Roofing felt. Brick. Catalan Rasilla. Concrete. Terraces. Roofs. Walls. Medianeras. Tkrom Waterproofing

### PROPERTIES

- High elasticity, does not crack or cracking
- Resists contraction and expansion
- Fully waterproof
- Good water resistance
- Good adhesion
- Passable in areas with limited passage
- Specially for warm areas

### TECHNICAL DATA

#### CLASSIFICATION ACCORDING TO UNE-EN-1062

|                         |  |                                 |           |
|-------------------------|--|---------------------------------|-----------|
| Finishing               | SEMIBRILLO                             | UNE-EN 1062-1                   |           |
| Colour                  | Transparent                            |                                 |           |
| 60° Brightness          | 80 ± 10                                | ISO 2813                        |           |
| Viscosity               | 20 ± 5 Pa·s (20 rpm, R6)               | ASTM D 2196-10                  |           |
| Density                 | 1,03 ± 0,05 g/ml                       | ISO 2811-1                      |           |
| Solids by volume        | 45 ± 2%                                | ISO 23811                       |           |
| Theoretical performance | 0.33 kg/m <sup>2</sup> at 150 µm dry   | ISO 23811                       |           |
| Fire classification     | Broof (t1)                             | EN 13501-1: 2018                | 4111T20-2 |
| VOC                     | <1 g/L. EU maximum permitted: 140 g/L. | 2004/42/II A Classification (i) |           |
| Diluent                 | Water                                  |                                 |           |
| Dilution                | <5%                                    |                                 |           |
| Repainting time         | 14-16 hours                            |                                 |           |
| Drying time             | Touch-drying                           | 4-8 hours                       | UNE 48301 |
|                         | Total drying                           | 7 days                          |           |
|                         | Washing:                               | 25-30 days                      |           |
| Cleaning                | Water                                  |                                 |           |

The specified technical data may vary in case of material tinting.  
1/4

## PREPARATION OF THE SUBSTRATE

---

### GENERAL RECOMMENDATIONS

---

Outdoors, do not apply if rain is expected, in full midday sun or on humid days.

#### TARPAULINS:

---

Moisture should be treated with care, likewise for entrapped air, check roughness and finish before cladding work commences. Always use a glass mesh reinforced system. Clean with pressurised water and use a suitable biocide. All cracks should be sealed with TKROM IMPERMEABILIZANTE ACRILICO INCOLORO beforehand to give security to the waterproofing. If the failure has occurred in the joining of the fabrics, the problem can be solved by sealing them by applying a generous coat of TKROM COVERS OR ANTIGOTHERAS FIBRA. Subsequently, after this application has dried, 2 coats of TKROM IMPERMEABILIZANTE should be applied over the joint of the asphalt membranes, at least 10cm, in the same way for surfaces that have already been painted. If there is any suspicion of possible failure of the fabric in areas other than the joints, clean the entire surface thoroughly and proceed as indicated for new surfaces.

#### OLD CONTINUOUS COAT WATERPROOFING:

---

Fill any cracks and fissures with TKROM IMPERMEABILIZANTE mixed with fine washed sand, in a 2:1 ratio, applied with a flat trowel, or with TKROM ANTIGOTERAS 2C, in the same way. Once dry, apply a coat of TKROM IMPERMEABILIZANTE to the entire surface. To obtain a high guarantee of waterproofing, place a mesh between the first and second coat. Afterwards, apply a second coat of TKROM IMPERMEABILIZANTE, transversally to the direction of the first coat, obtaining the desired minimum thickness of 0.4 mm with this second coat. It is important to also waterproof the vertical walls, at least at a height of 15 to 20 cm.

#### CONSIDERATIONS FOR OTHER MEDIA:

---

##### CONCRETE:

---

The surface must be dry and have the necessary air maturing time (minimum 4 weeks). The substrate must comply with the requirements of the standard for concrete UNE-EN ISO 1504-2. If the surface has a disintegrated or dusty appearance, apply 1 coat of TKROM FIJATIVO F1 beforehand.

##### STONE, BRICK, SLATE OR TILE:

---

Pressure wash and use a biocide if necessary. Follow conventional preparation procedures. In the case of slate or tile, treat with a special reinforcement before applying the system.

##### BITUMINOUS MEMBRANE:

---

Replace the bituminous membrane in poor condition. Treat blisters by opening and removing occluded water. Dry and apply a fiberglass patch with TKROM WATERPROOFING. Then apply the waterproofing.

##### PLASTIC:

---

Apply the waterproofing system directly. An adhesion test is recommended before applying the treatment.

##### MASONRY PLASTERING AND RENDERING:

---

The state of the substrate must comply with the standard for mortars UNE-EN 998-2, and following its specifications, the adhesion value to the substrate must be in accordance with that specified in the manufacturer's CE marking. In no case should it be less than 0.2 N/mm<sup>2</sup>. The average value must be 0.3 N/mm<sup>2</sup>.

##### PAINTINGS:

---

It is not recommended to apply on paints, they must be previously removed by water or sand blasting. The quality of old coatings is important. Their adhesion should not be less than 0.7 N/mm<sup>2</sup>, and the average value should be higher than 1N/mm<sup>2</sup> (ISO 1504-2). Poor adhesion: Use suitable mechanical means to remove old coatings. The substrate must be suitably prepared to accept the new finish. Correct adhesion: Clean the entire surface with a steam jet or high pressure water jet.

##### CLEANING OF THE SUPPORT:

---

It is necessary to eliminate all those elements that, if they remain while we apply our treatment, may be harmful to the durability and resistance of the treatment. As these are areas with a high level of humidity for long periods of time, the presence of microorganisms is more than usual, which must be properly eliminated prior to waterproofing. To do this, we will eliminate mould and moss, using mechanical methods such as spatulas, metal scourers, brushes and applying 10-20% dilutions of bleach by brush or spray.

Once the surface has been cleaned of all traces of bleach, then apply TKROM Reinforcing Cleaner. If the attack of microorganisms is very severe, this treatment can be repeated, and it is also very convenient in these cases to apply, after 24-48 hours, a coat of TKROM Sealer-Sanitizer Primer. After cleaning with water, wait 24-48 hours before proceeding with the following works.

#### SURFACE CONSOLIDATION:

Damage caused by the ageing of the surface itself, as well as possible damage caused during cleaning and disinfection, must be repaired beforehand.

For this purpose, we recommend the use of the product "TKROM PLAST", which is very easy to apply and sand, following as always the preparation and application instructions described in its technical data sheet.

If the terrace to be waterproofed has a ceramic or tiled floor, it is advisable to reconstruct the joints between tiles, prior to the waterproofing treatment. For this purpose, a cement grout shall be used. Other critical points where waterproofing defects may occur are: Joints between vertical walls and the terrace. Vertical wall ledges. Joints of ventilation or drainage ducts and pipes. Drainage grilles. Expansion joints. Vertical walls surrounding the terrace.

In these critical points, special care should be taken in cleaning and reconstruction work. TKROM Antigotas 2C can be used, or the application of TKROM IMPERMEABILIZANTE can be reinforced by incorporating fibreglass mesh between the coats of the waterproofing. Once the surface has been cleaned and repaired, we can begin with the waterproofing of the terrace.

#### IMPLEMENTATION SYSTEM:

| SYSTEM   | PRODUCT                               | THEORETICAL COVERAGE   | DILUTION    | LAYERS |
|--|---------------------------------------|--|-------------|--------|
| <b>PRIMER</b> (very porous substrates, unpainted aged surfaces, substrates with efflorescence) | TKROM FIJATIVO F4                     | 14-18 m <sup>2</sup> /L  | 1:4 water   | 1 o 2  |
|  | TKROM FIJADOR AL AGUA PLIOTEC         | 10-14 m <sup>2</sup> /L  | No dilution | 1 o 2  |
| <b>COATING</b> (Surfaces with low absorbency, aged paints)                                     | TKROM FIJATIVO F1                     | 14-18 m <sup>2</sup> /L  | 1:1 water   | 1 o 2  |
| <b>COATING</b> (Substrates with micro-organisms)   | TKROM LIMPIADOR REFORZANTE            | n.a.   | No dilution | 1 o 2  |
|  | TKROM IMPRIMACION SELLADORA-SANEADORA | 14-18 m <sup>2</sup> /L  | No dilution | 1 o 2  |
| <b>PRIMING</b>   | TKROM IMPERMEABILIZANTE DILUIDO       | 3 m <sup>2</sup> /L (150 µm minimum final thickness)             | 3:1 water   | 1 o 2  |
| <b>FINISH</b>  | TKROM IMPERMEABILIZANTE               | 2.3 m <sup>2</sup> /L and layer (400 µm minimum final thickness) | No dilution | 2      |

## CONDITIONS OF APPLICATION

|                                    |  |
|------------------------------------|--|
| <b>Substrate and Ambient Temp.</b> | Min. +5°C / Max. +35°C   |
| <b>Ambient humidity</b>            | Max. 80% of the total  |
| <b>Humidity Substrate</b>          | Dry substrate with humidity < 4%. Cement mortars, allow to set completely (28 days minimum). Cement-based products, allow to dry for at least 4 days before coating. |
| <b>Rocio Point</b>                 | The substrate temperature must be at least 3°C above the dew point to reduce the risk of detachment or efflorescence.  |

## RECOMMENDATIONS FOR IMPLEMENTATION

|                              |  |
|------------------------------|--|
| <b>Product preparation</b>   | Stir until the product is well homogenised.  |
| <b>Method of application</b> | It can be applied by brush, short nap roller or airless spraying. For airless spraying, use the following: 150 bar pressure, 0.38-0.53 mm nozzle, 50°-80° angle. Due to the high thixotropy of the product, high spray pressures are not required. |
| <b>Preparation</b>           | Shake to homogenise the product. Adjust the viscosity with water. The second coat of the product should be applied perpendicular to the first coat to achieve optimum opacity.   |

## ADDITIONAL DATA

|                          |   |
|--------------------------|---|
| <b>Health and safety</b> | For any information concerning safety issues in the use, storage, transport and disposal of this product, users should consult the labelling and the most recent version of the MSDS, which contains safety, ecological and toxicological information on the product. |
|--------------------------|---|

Safety Data Sheet: Please refer to the most recent version. LER CODE: 08 0112 | WASTE TYPE: NON-HAZARDOUS

|                |   |
|----------------|---|
| <b>Storage</b> | The stability of the product in its original unopened containers, at ambient temperatures of not more than 30 °C and not less than 5 °C shall be 24 months from the date of manufacture. Storage shall be in a cool, dry place, in their original containers, tightly closed, undamaged and protected from frost and direct sunlight. |
|----------------|---|

|                       |                        |
|-----------------------|------------------------|
| <b>Tariff heading</b> | TARIC code: 3209 10 00 |
|-----------------------|------------------------|

|             |  |
|-------------|--|
| <b>NOTE</b> | Note: The data indicated in this technical data sheet may be modified according to possible variations in formulation and in any case they express indicative values which do not exempt from carrying out the appropriate tests of suitability of the product for a specific job. |
|-------------|--|