



BLOCK STAIN

SALES FORMAT

4L, 750ML

DESCRIPTION

Matt acrylic paint with stain covering action which, thanks to the technology used in its formulation, acts effectively as a blocking barrier against all types of stains; damp, smoke, nicotine, grease, among others.

SCOPE OF APPLICATION

Inside
 Building materials
 Cement, Concrete
 Bedrooms, Kitchens, Bathrooms
 Garages, Basements
 Wineries

PROPERTIES

- Excellent hiding power
- Very fast drying
- High insulating power
- Very good adhesion
- Good whiteness
- Repaintable with plastic paints
- Matt finish
- Easy to apply

TECHNICAL DATA

| | | |
|----------------------|------------------|-------------------|
| Chemical composition | Acrylic resins | |
| Colour | White | |
| Finishing | Mate | UNE-EN ISO 2813 |
| Brightness 85°. | 10 ± 2 | UNE-EN ISO 2813 |
| Density | 1,61 ± 0,05 g/ml | UNE-EN ISO 2811-1 |
| Viscosity | 100 ± 10 KU | UNE 48076 |
| Solids by volume | 53 ± 2% | UNE-EN ISO 23811 |

| | | |
|-----|---|---------------------------------|
| VOC | < 500 g/L . Maximum value allowed by the EU: 500 g/L. | 2004/42/II A classification (i) |
|-----|---|---------------------------------|

| | |
|-------------------------|---|
| Theoretical performance | 10-12 m ² /L - 5-7 m ² /Kg (50 microns dry) |
|-------------------------|---|

| | | |
|--------------|--------------|----------|
| Drying times | Touch-drying | 5-10 min |
| | Total drying | 2 hours |

| | |
|-----------------|-------------|
| Repainting time | from 1 hour |
|-----------------|-------------|

| | |
|----------|---------------------------------------|
| Dilution | 0-10% depending on application system |
|----------|---------------------------------------|

| | |
|---------|--|
| Diluent | TKROM DISOL. 376 ANTIOXIDANT or CHLOROCAUCHO DISOL.350 |
|---------|--|

| | |
|----------|--------------------------------|
| Cleaning | TKROM DISOLVENTE UNIVERSAL 302 |
|----------|--------------------------------|

PREPARATION OF THE SUBSTRATE

NEW SURFACES

On new, firm, clean and dry surfaces, no preparation of the substrate is necessary, apply TKROM BLOCKSTAIN directly.

ALREADY PAINTED SURFACES

On already painted surfaces, if the paintwork is in good condition, apply the product directly. For paintwork in poor condition, remove poorly adhering or defective parts, dust, grease and dirt. If there is mould, mechanically clean the area affected by microorganisms using scrapers, brushes, scouring pads, etc. in order to remove the stains and then apply TKROM LIMPIADOR REFORZANTE and allow to dry.

CONDITIONS OF APPLICATION

| | |
|----------------------------|---|
| Substrate Temp. | Min. + 5°C / Max. + 35°C |
| Ambient Temperature | 5°C / 35°C |
| Rocio Point | The substrate temperature must be at least 3°C above the dew point to reduce the risk of detachment or efflorescence. |

APPLICATION SYSTEM

| APPLICATION SYSTEM | PRODUCT | PERFORMANCE | DILUTION | LAYERS |
|--------------------|------------------|---|---|--------|
| PRIMING | TKROM BLOCKSTAIN | 10-12 m ² /L - 5-7 m ² /Kg (50 microns dry) | 0-10% TKROM TKROM DISOL. 376 ANTIOXIDANT o DISOL.350 CHLOROCAUCHO | 1 o 2 |

RECOMMENDATIONS FOR IMPLEMENTA-

Product preparation: Stir until the product is well homogenised. Stir again periodically. Adjust viscosity. In long processes evaporation will occur, readjust viscosity.

Method of application: Can be applied by brush or roller.

Apply the product evenly to achieve perfect concealment of stains and homogeneous coverage.

ADDITIONAL DATA

Health and safety Highly flammable. For any information concerning safety issues in the use, storage, transport and disposal of this product, users should consult the labeling and the most recent version of the MSDS, which contains physical, ecological, toxicological and other relevant data. WASTE: HAZARDOUS. LER CODE: 080111

Storage The stability of the product in its original unopened containers, at ambient temperatures of not more than 30 °C and not less than 5 °C shall be 24 months from the date of manufacture. Storage shall be in a cool, dry place, in their original containers, tightly closed, undamaged and protected from frost and direct sunlight.

Tariff heading TARIC code: 3208 20 90

Note Note: The data indicated in this technical data sheet may be modified according to possible variations in formulation and in any case express indicative values that do not exempt from carrying out the appropriate tests to check the suitability of the product for a specific job. For any doubts regarding the treatment of the surfaces mentioned above or for the painting of other specific materials not covered in this data sheet, consult the appropriate treatment with technical personnel accredited by the TKROM GROUP.