



# IMPRIMACIÓN SUPERLITE EXTERIOR

## SALES FORMAT

15L, 4L

### DESCRIPTION

Primer for facades, based on special resins in solution. Due to its exceptional adhesion, penetration capacity and resistance to alkaline agents, as well as its microporous structure, which allows the substrate to breathe, it is the ideal base coat for subsequent painting with TKROM SUPERLITE EXTERIOR.

### SCOPE OF APPLICATION

Indoor/Outdoor  
Masonry surfaces  
Cement  
Brick or plaster walls  
Concrete

### PROPERTIES

- Toilet once dry
- Excellent applicability
- High penetration power
- Very good adhesion
- No sanding required for repainting
- Regulates absorption
- Microporous
- High breathability

### TECHNICAL DATA

Chemical composition	Special acrylic resins	
Colour	White	
Finishing	Mate	
Density	1.57-1.61 g/ml	UNE-EN ISO 2811-1
Viscosity	2.8-5.5 mPa.s	ASTM D 2196-10
Solids by volume	47-49%	UNE - EN ISO 23811
VOC	< 500 g/L . Maximum value allowed by the EU: 500 g/L.	2004/42/II A classification (i)
<b>Theoretical performance</b>	6-8 m <sup>2</sup> /L (70 microns dry)	
<b>Drying times</b>	<b>Touch-drying</b>	15-20 min
	<b>Total drying</b>	3 h
<b>Repainting time</b>	6 h	
<b>Dilution</b>	0-10% depending on application system	
<b>Diluent</b>	TKROM DISOL. CLOROCAUCHO 350 / TKROM DISOL. SINTETICOS 345	
<b>Cleaning</b>	TKROM DISOLVENTE UNIVERSAL 302	

## PREPARATION OF THE SUBSTRATE

### GENERAL

Outdoors, do not apply if rain is expected, in full midday sun or on humid days.

### SURFACES OF CEMENT, CONCRETE AND MASONRY IN GENERAL

Check the state of the wall surface and repair any imperfections with the appropriate mortars or products. Remove any remaining lime or tempera paints that may exist. Apply one or two coats of TKROM IMPRIMACION SUPERLITE.

### CONDITIONS OF APPLICATION

<b>Substrate Temp.</b>	Min. + 5°C / Max. + 35°C
<b>Ambient Temperature</b>	5°C / 35°C
<b>Rocio Point</b>	The substrate temperature must be at least 3°C above the dew point to reduce the risk of detachment or efflorescence.

### APPLICATION SYSTEM

APPLICATION SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
<b>PRIMER (Cement, Concrete and Masonry in general)</b>	TKROM IMPRIMACION SUPERLITE EXTERIOR	6-8 m <sup>2</sup> /L and layer	10% ACCORDING TO TKROM DTE CLOROCAUCHO 350 / TKROM DTE SINTETICOS 345	1 o 2
<b>FINISH</b>	TKROM SUPERLITE EXTERIOR	6-8 m <sup>2</sup> /L and layer	5-20% DEPENDING ON SYSTEM TKROM DTE CLOROCAUCHO 350/ TKROM DTE SINTETICOS 345	1 o 2

## RECOMMENDATIONS FOR IMPLEMENTA-

<b>Product preparation:</b>	Stir until the product is well homogenised. Stir again periodically. Adjust viscosity. In long processes evaporations will occur, readjust viscosity. An excessively energetic solvent may make it advisable to reduce the proportion of solvent.
<b>Method of application:</b>	It can be applied by brush, roller or airless spray gun. For application by brush, roller or airless spray gun, dilute the product with a small quantity (0-10%) of TKROM DISOLVENTE CLOROCAUCHO Y SUPERLITE EXTERIOR 350.

## ADDITIONAL DATA

<b>Health and safety</b>	For any information concerning safety issues in the use, storage, transport and disposal of this product, users should refer to the labelling and the most recent version of the MSDS, which contains physical, ecological, toxicological and other relevant data. WASTE: HAZARDOUS. LER CODE: 080111
<b>Storage</b>	The stability of the product in its original unopened containers, at ambient temperatures of not more than 30°C and not less than 5°C, shall be 24 months from the date of manufacture. Storage shall be in a cool, dry place, in their original containers, well closed, undamaged and protected from frost and direct sunlight.
<b>Tariff heading</b>	TARIC code: 3208 20 90
<b>Note</b>	Note: The data indicated in this technical data sheet may be modified according to possible variations in formulation and in any case express indicative values that do not exempt from carrying out the appropriate tests to check the suitability of the product for a specific job. For any doubts regarding the treatment of the surfaces mentioned above or for the painting of other specific materials not covered in this data sheet, consult the appropriate treatment with technical personnel accredited by the TKROM GROUP.